



Leather — Physical and mechanical tests — Determination of tear load —

Part 1: Single edge tear

*Cuir — Essais physiques et mécaniques — Détermination de la force de déchirement —
Partie 1: Déchirement d'un seul bord*

[Revision of first edition (ISO 3377-1:2002)]

ICS 59.140.30

ISO/CEN PARALLEL PROCESSING

This draft has been developed within the European Committee for Standardization (CEN), and processed under the **CEN-lead** mode of collaboration as defined in the Vienna Agreement.

This draft is hereby submitted to the ISO member bodies and to the CEN member bodies for a parallel five-month enquiry.

Should this draft be accepted, a final draft, established on the basis of comments received, will be submitted to a parallel two-month approval vote in ISO and formal vote in CEN.

This draft International Standard is submitted to all ISO member bodies for voting, as a standard prepared by an international standardizing body in accordance with Council Resolution 42/1999. The proposer, International Union of Leather Technologists and Chemists (Commission IUP, IULTCS), has been recognized by the ISO Council as an international standardizing body for the purpose of Council Resolution 42/1999.

In accordance with the provisions of Council Resolution 15/1993 this document is circulated in the English language only.

Conformément aux dispositions de la Résolution du Conseil 15/1993, ce document est distribué en version anglaise seulement.

To expedite distribution, this document is circulated as received from the committee secretariat. ISO Central Secretariat work of editing and text composition will be undertaken at publication stage.

Pour accélérer la distribution, le présent document est distribué tel qu'il est parvenu du secrétariat du comité. Le travail de rédaction et de composition de texte sera effectué au Secrétariat central de l'ISO au stade de publication.

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

Copyright notice

This ISO document is a Draft International Standard and is copyright-protected by ISO. Except as permitted under the applicable laws of the user's country, neither this ISO draft nor any extract from it may be reproduced, stored in a retrieval system or transmitted in any form or by any means, electronic, photocopying, recording or otherwise, without prior written permission being secured.

Requests for permission to reproduce should be addressed to either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Reproduction may be subject to royalty payments or a licensing agreement.

Violators may be prosecuted.

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Principle	1
4 Apparatus	1
5 Sampling and sample preparation	2
6 Procedure	2
7 Test report	3

DRAFT

2010

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 3377-1 was prepared by the Physical Tests Commission of the International Union of Leather Technologists and Chemists Societies (IUP Commission, IULTCS) in collaboration with the European Committee for Standardisation (CEN) Technical Committee CEN/TC 289, *Leather*, the secretariat of which is held by UNI, in accordance with the agreement on technical co-operation between ISO and CEN (Vienna Agreement).

This second edition cancels and replaces the first edition which has been technically revised.

ISO 3377 consists of the following parts, under the general title *Leather — Physical and mechanical tests - Determination of tear load*:

- *Part 1: Single edge tear*
- *Part 2: Double edge tear*

Leather — Physical and mechanical tests — Determination of tear load —

Part 1: Single edge tear

1 Scope

This part of ISO 3377 specifies a method for determining the tear strength of leather using a single edged tear. The method is sometimes described as a trouser tear. It is applicable to all types of leather.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2418, *Leather - Chemical, physical and mechanical and fastness tests - Sampling location*

ISO 2419, *Leather - Physical and mechanical tests - Sample preparation and conditioning*

ISO 2589, *Leather - Physical and mechanical tests - Determination of thickness*

ISO 7500-1, *Metallic materials – Verification of static uniaxial testing machines – Part 1: Tension/compression testing machines – Verification and calibration of the force-measuring system*

3 Principle

A rectangular test specimen partially slit from one short edge is pulled so that a tear is propagated from the end of the slit. The mean force exerted during separation of the test piece is recorded.

4 Apparatus

4.1 Tensile testing machine, with:

- a force range appropriate to the specimen under test;
- a means of recording the force to an accuracy of at least 2% as specified by Class 2 of ISO 7500-1;
- a uniform speed of separation of the jaws of $100 \text{ mm/min} \pm 20 \text{ mm/min}$;
- a means of recording the force - e.g. as an extension curve;
- jaws, minimum width $50 \text{ mm} \pm 2 \text{ mm}$.

4.2 Thickness gauge, as specified in ISO 2589.

4.3 Press knife, as specified in ISO 2419, capable of cutting rectangular test pieces as shown in Figure 1 in one operation. All parts of the press knife shall lie in the same plane.




Figure 1 — Test piece for single edge tear

Table 1 – Dimensions of test piece

All dimensions in millimetre (tolerance ± 1 mm)

Designation	a	b	c	d
Standard	70	40	b/2	20
Large	100	50	b/2	50

If large test pieces are used, the size of the test piece has to be mentioned in the test report.

NOTE For manual evaluation it is advantageous to use the large specimen.

5 Sampling and sample preparation

5.1 Sample in accordance with ISO 2418. From the sample, cut 6 test pieces in accordance with ISO 2419, 3 test pieces with the longer sides parallel to the backbone and 3 test pieces with the longer sides perpendicular to the backbone.

NOTE If there is a requirement for more than two hides or skins to be tested in one batch, then only one test piece in each direction need be taken from each hide or skin, provided that the overall total is not less than three test pieces in each direction.

5.2 Condition the test pieces in accordance with ISO 2419.

5.3 Measure the thickness of the test pieces in accordance with ISO 2589.

6 Procedure

6.1 Set the jaws of the tensile testing machine (4.1) so that clamps are at a suitable distance to firmly hold the test piece (e. g. 50 mm).

6.2 Clamp one leg of the test piece in one jaw of the tensile test machine (see Figure 2). Fold the other leg through 180° and clamp in the other jaw. Ensure that the long edges of the test piece are parallel to the testing direction of the machine.




Figure 2 — Method of fixing test piece in jaws of the tensile test machine

6.3 Run the tensile test machine until the test piece is torn apart and record the force-extension plot.

6.4 Determine the tear load of the test piece as the arithmetic mean of the forces on the peak trace proceeding in the following way:

Divide the peak trace into four equal parts beginning with the first peak and ending with the last peak. The first and the last part shall not be used for the calculation of the mean value. Determine the tear load as the mean value in Newton in the two remaining middle subsections. In electronic evaluation all the data points of the force in the middle subsections of the diagram are considered.

In case of manual calculation select and note the two highest peaks (maxima) and the two lowest valleys (minima) from each of the middle subsections (i.e. 8 values). Peaks and valleys suitable for calculation are characterised by a 10% minimum rising and falling of force. Tear load is defined by the arithmetic mean of these values. The use of this evaluation method shall be mentioned in the test report.

NOTE Depending on the evaluation procedure a different number of values are taken into consideration as a calculation basis. Consequently, the results of the two calculation methods may differ. Being more precise, the electronic method shall be preferred.

NOTE In some cases, due to the lack of distinguishable peaks and valleys, the evaluation of the diagram can be difficult. Such results have to be rejected and the test has to be repeated.

NOTE In case of litigation, tear load must be determined only using the electronic evaluation on test pieces with standard dimensions (4.3).

6.5 Repeat 6.2 to 6.4 for other test pieces.

7 Test report

The test report shall include the following:

- a) reference to this part of ISO 3377, i.e. ISO 3377-1;
- b) the thickness of the leather in mm;

- c) the mean tear load in Newton (N) to the nearest 0,1 N for test pieces with the longer edge cut parallel to the backbone;
- d) the mean tear load in Newton (N) to the nearest 0,1 N for the test pieces with the longer edge perpendicular to the backbone;
- e) the average tear load to the nearest 0,1 N (i.e., the arithmetic mean of c and d), if required by customer or in specifications;
- f) the standard atmosphere used for conditioning and testing, as given in ISO 2419;
- g) any deviations from the method specified in this part of ISO 3377;
- h) full details for identification of the sample and any deviations from ISO 2418 with respect to sampling.

DRAFT

2010